

PACKAGING REQUIREMENTS AND QUALITY ASSURANCE PROVISIONS FOR MIL-R-44398, RATION SUPPLEMENT, FLAMELESS RATION HEATER FOR ASSEMBLY OF MEAL, READY-TO-EAT, INDIVIDUAL FOR PREPOSITIONED STOCK

SECTION D

D-1 PACKAGING

A. Packaging. When specified, the Flameless Ration Heater (FRH) in the specified heater bags shall be packed in a preformed pouch as described below. The packaging of the heaters and heater bags into the preformed pouches shall occur in the heater manufacturer's plant immediately subsequent to insertion of heaters into heater bags.

(1) Preformed pouches.

a. Pouch material. The preformed pouch shall be fabricated from 0.002 inch thick ionomer or polyethylene film laminated or extrusion coated to 0.00035 inch thick aluminum foil which is then laminated to 0.0005 inch thick polyester. The three plies shall be laminated with the polyester on the exterior of the pouch. All tolerances for thickness of pouch material shall be plus or minus 20 percent. The material shall show no evidence of delamination, degradation, or foreign odor when heat sealed or fabricated into pouches. The material shall be suitably formulated for food packaging and shall not impart an odor or flavor to the product. The complete exterior surface of the pouch shall be uniformly colored in the range of 20219, 30219, 30279, 30313, 30324, or 30450 of FED-STD-595.

b. Pouch construction. The pouch shall be a flat style preformed pouch having maximum inside dimensions of 5 inches wide by 7-1/4 inches long ($\pm 1/8$ inch in each dimension). The pouch shall be made by heat sealing three edges with 3/8 inch (-1/8 inch, +3/16 inch) wide seals. The heat seals shall be made in a manner that will assure hermetic seals. The side and bottom seals shall have an average seal strength of not less than 6 pounds per inch of width and no individual specimen shall have a seal strength of less than 5 pounds per inch of width when tested as specified in E-5, A,(4),a. Alternatively, the filled and sealed pouch shall exhibit no rupture or seal separation greater than 1/16 inch or seal separation that reduces the effective closure seal width to less than 1/16 inch when tested for internal pressure resistance as specified in E-5, A,(4),c. A tear nick or tear notch shall be provided on one outside edge or two opposite outside edges of the pouch to facilitate easy opening of the filled and sealed pouch. A 1/8 inch (+1/16 inch) wide lip may be incorporated at the open end of the pouch to facilitate opening and filling of the pouch.

c. Pouch filling and sealing. When specified, the FRH shall be inserted into the pouch and heat sealed. The closure seal shall be free of foldover wrinkles or entrapped matter that reduces the effective closure seal width to less than 1/16 inch. Seals shall be free of impression or design on the seal surface that would conceal or impair visual detection of seal defects. The average seal strength shall be not less than 6 pounds per inch of width and no individual specimen shall have a seal strength of less than 5 pounds per inch of width when tested as specified in E-5,A,(4),b. Alternatively, the filled and sealed pouch shall exhibit no rupture or seal separation greater than 1/16 inch or seal separation that reduces the effective closure seal width to less than 1/16 inch when tested for internal pressure resistance as specified in E-5,A,(4),c.

D-2 LABELING

A. Pouches. Each pouch shall be clearly printed or stamped, in a manner that does not damage the pouch, with permanent black ink or other, dark, contrasting color which is free of carcinogenic elements. The information shall be located on the body of the pouch not closer than 1/16 inch to any seal. If a non-contact type printer is used, the information may be located anywhere on the pouch (in one complete print), except the closure seal area. The label shall contain the following information:

Product Name (letters not less than 1/8 to 7/16 inch block letters inch high)
Date 1/

Contractor's name and address

1/ Each pouch shall have the date of pack noted by using a four-digit code beginning with the final digit of the current year followed by the three digit Julian day code. (Example, 12 April 2000 would be coded as 0103). The Julian day code shall represent the day the product was packaged into the pouch.

D-3 PACKING

A. Packing for shipment to ration assembler. Heaters shall be packed in a manner to ensure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. The shipping container must conform with all provisions of 49 CFR Parts 171-180 (Hazardous Materials Regulations) for Division 4.3, Packing Group I materials, unless the contractor can certify that the heater is other than such or the Department of Transportation authorizes an official exemption from these provisions. The shipping container shall be constructed in accordance with ASTM D 5118 and closed in accordance with ASTM D 1974. When metal fasteners are used in the manufacture's joint or setup of the fiberboard box, the fasteners on the inside of the box shall be covered with tape or paperboard to protect contents from mechanical damage. If fiberboard shipping containers are not specified to be palletized in unit loads, each shipping container shall be provided with a Material Safety Data Sheet (MSDS) securely attached to one side in a clear plastic, self-adhering sleeve or with tape.

D-4 MARKING

A. Shipping Containers. In addition to any special marking required by the contract or purchase order, unit packs, shipping containers, and palletized unit loads shall be marked in accordance with DPSC Form 3556. The top of the shipping container shall be clearly marked as follows:

OPEN CAREFULLY IF USING KNIFE TO AVOID SLITTING CONTENTS

For level C packed heaters, shipping containers and palletized unit loads shall be marked in accordance with 49 CFR Parts 171-180, for Division 4.3, Packing Group I materials, unless officially exempted by the Department of Transportation.

SECTION E INSPECTION AND ACCEPTANCE

The following quality assurance criteria, utilizing ANSI/ASQC Z1.4-1993, Sampling Procedures and Tables for Inspection by Attributes, are required. When required, the manufacturer shall be required to provide the certificate(s) of conformance to the appropriate inspection activity. Certificate(s) of conformance not provided shall be cause for rejection of the lot.

A. Definitions.

(1) Critical defect. A critical defect is a defect that judgment and experience indicate would result in hazardous or unsafe conditions for individuals using, maintaining, or depending on the item; or a defect that judgment and experience indicate is likely to prevent the performance of the major end item, i.e., the consumption of the ration.

(2) Major defect. A major defect is a defect, other than critical, that is likely to result in failure, or to reduce materially the usability of the unit of product for its intended purpose.

(3) Minor defect. A minor defect is a defect that is not likely to reduce materially the usability of the unit of product for its intended purpose, or is a departure from established standards having little bearing on the effective use or operation of the unit.

E-5 PACKAGING AND PACKING MATERIALS

A. Packaging.

(1) Pouch material certification. Material listed below may be accepted on the basis of a contractor's certification of conformance to the indicated requirements. In addition, compliance to the requirements for inside pouch dimensions and dimensions of manufacturer's seals may be verified by certificate of conformance.

<u>Requirement</u>	<u>Requirement Paragraph</u>	<u>Test procedure</u>
Thickness of films for Laminated material	D-1,A,(1),a	As specified in ASTM D 2103 <u>1/</u>
Aluminum foil thickness Laminated material Identification and construction	D-1,A,(1),a D-1,A,(1),a	As specified in ASTM B 479 <u>2/</u> Laboratory evaluation
Color of laminated material	D-1,A,(1),a	Visual evaluation by FED-STD-595 <u>3/</u>

1/ ASTM D 2103 Specification for Polyethylene Film and Sheeting

2/ ASTM B 479 Specification for Annealed Aluminum Foil For Flexible Barrier Application

3/ FED-STD-595 Colors Used in Government Procurement

(2) Unfilled preformed pouch certification. A certification of conformance may be accepted as evidence that unfilled pouches conform to the requirements specified in D-1,A,(1) a and b. When deemed necessary by the USDA, testing of the unfilled preformed pouches for seal strength shall be as specified in E-5,A,(4),a.

(3) Filled and sealed pouch examination. The filled and sealed pouches shall be examined for the defects listed in table I. The lot size shall be expressed in pouches. The sample unit shall be one pouch. The inspection level shall be I and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 0.65 for major defects and 4.0 for minor defects.

TABLE I. Filled and sealed pouch defects 1/

Category		Defect
<u>Major</u>	<u>Minor</u>	
101		Tear, hole, or open seal.
102		Seal width less than 1/16 inch. <u>2/</u>
103		Presence of delamination. <u>3/</u>
104		Unclean pouch. <u>4/</u>
105		Pouch has foreign odor.
106		Any impression or design on the heat seal surfaces which conceals or impairs visual detection of seal defects. <u>5/</u>
	201	Label smudges, is missing, incorrect, or illegible.
	202	Tear notch or serrations missing or does not facilitate opening.
	203	Seal width less than 1/8 inch but greater than 1/16 inch.
	204	Presence of delamination. <u>3/</u>

1/ Any evidence of rodent or insect infestation shall be cause for rejection of the lot.

2/ The effective closure seal is defined as any uncontaminated, fusion bonded, continuous path, minimum 1/16 inch wide, from side seal to side seal that produces a hermetically sealed pouch.

3/ Delamination defect classification:

Major - Delamination of the outer ply in the pouch seal area that can be propagated to expose aluminum foil at the food product edge of the pouch after manual flexing of the delaminated area. To flex, the delaminated area shall be held between the thumb and forefinger of each hand with both thumbs and forefingers touching each other. The delaminated area shall then be rapidly flexed 10 times by rotating both hands in alternating clockwise- counterclockwise directions. Care shall be exercised when flexing delaminated areas near the tear notches to avoid tearing the pouch material. After flexing, the separated outer ply shall be grasped between thumb and forefinger and gently lifted toward the food product edge of the seal or if the separated area is too small to be held between thumb and forefinger, a number two stylus shall be inserted into the delaminated area and a gentle lifting force applied against the outer ply. If separation of the outer ply can be made to extend to the product edge of the seal with no discernible resistance to the gentle lifting, the delamination shall be classified as a major defect. Additionally, spot delamination of the outer ply in the body of the pouch that is able to be propagated beyond its initial borders is also a major defect. To determine if the laminated area is a defect, use the following procedure: Mark the outside edges of the delaminated area using a bold permanent marking pen. Open the pouch and remove the contents. Cut the pouch transversely not closer than 1/4 inch (\pm 1/16 inch) from the delaminated area. The pouch shall be flexed in the area in question using the procedure described above. Any propagation of the delaminated area, as evidenced by the delaminated area exceeding the limits of the outlined borders, shall be classified as a major defect.

Minor - Minor delamination of the outer ply in the pouch seal area is acceptable and shall not be classified as a minor defect unless it extends to within 1/16 inch of the food product edge of the seal. All other minor outer ply delamination in the pouch seal

14 NOVEMBER 2000

area or isolated spots of delamination in the body of the pouch that do not propagate when flexed as described above shall be classified as minor defects.

4/ Outer packaging shall be free from foreign matter which is unwholesome, has the potential to cause pouch damage (for example, glass, metal filings) or generally detracts from the clean appearance of the pouch. The following examples shall not be classified as defects for unclean:

a. Foreign matter which presents no health hazard or potential pouch damage and which can be readily removed by gently shaking the package or by gently brushing the pouch with a clean dry cloth.

b. Dried product which affects less than 1/8 of the total surface area of one pouch face (localized and aggregate).

c. Water spots.

5/ If doubt exists as to whether or not the sealing equipment leaves an impression or design on the closure seal surface that could conceal or impair visual detection of seal defects, samples shall be furnished to the contracting officer for a determination as to acceptability.

(4) Seal testing. The pouch seals shall be tested for seal strength as required in a, b, or c, as applicable.

a. Unfilled preformed pouch seal testing. The seals of the unfilled preformed pouch shall be tested for seal strength in accordance with ASTM F 88 - Seal Strength of Flexible Barrier Materials. The lot size shall be expressed in pouches. The sample size shall be the number of pouches indicated by inspection level S-1. Three adjacent specimens shall be cut from each of the three sealed sides of each pouch in the sample. The average seal strength of any side shall be calculated by averaging the three specimens cut from that side. Any average seal strength of less than 6 pounds per inch of width or any test specimen with a seal strength of less than 5 pounds per inch of width shall be cause for rejection of the lot.

b. Pouch closure seal testing. The closure seals of the pouches shall be tested for seal strength in accordance with ASTM F 88. The lot size shall be expressed in pouches. The sample size shall be the number of pouches indicated by inspection level S-1. Three adjacent specimens shall be cut from the closure seal of each pouch in the sample. The average seal strength of the closure shall be calculated by averaging the three specimens cut from that closure. Any average seal strength of less than 6 pounds per inch of width or any test specimen with a seal strength of less than 5 pounds per inch of width shall be cause for rejection of the lot.

c. Internal pressure test. The internal pressure resistance shall be determined by pressurizing the pouches while they are restrained between two rigid plates. The sample size shall be the number of pouches indicated by inspection level S-1. If a three seal tester (one that pressurizes the pouch through an open end) is used, the closure seal shall be cut off for testing the side and bottom seals of the pouch. For testing the closure seal, the bottom seal shall be cut off. The pouches shall be emptied prior to testing. If a four-seal tester (designed to pressurize filled pouches by use of a hypodermic needle through the pouch wall) is used, all four seals can be tested simultaneously. The distance between rigid restraining plates on the four-seal tester shall be equal to the thickness of the product +1/16 inch. Pressure shall be applied at the approximate uniform rate of 1 pound per square inch gage (psig) per second until 14 psig pressure is reached. The 14 psig pressure shall be held constant for 30 seconds and then released. The pouches shall then be examined for separation or yield of the heat seals. Any rupture of the pouch or evidence of seal separation greater than 1/16 inch in the pouch manufacturer's seal shall be considered a test failure. Any seal separation that

reduces the effective closure seal width to less than 1/16 inch (see table I, footnote 2/) shall be considered a test failure. Any test failure shall be cause for rejection of the lot.

B. Packing.

(1) Shipping container and marking examination. The filled and sealed shipping containers shall be examined for the defects listed in table II below. The lot size shall be expressed in shipping containers. The sample unit shall be one shipping container fully packed. The inspection level shall be S-3 and the AQL, expressed in terms of defects per hundred units, shall be 4.0 for major defects and 10.0 for total defects.

TABLE II. Shipping container and marking defects

Category		Defect
<u>Major</u>	<u>Minor</u>	
101		Marking omitted, incorrect, illegible, or improper size, location sequence or method of application.
102		Inadequate workmanship. <u>1/</u>
	201	More than 40 pounds of product.

1/ Inadequate workmanship is defined as, but not limited to, incomplete closure of container flaps, loose strapping, inadequate stapling, improper taping, or bulged or distorted container.

SECTION J REFERENCE DOCUMENTS

DSCP FORMS

DPSC FORM 3556 Marking Instructions for Shipping Cases, Sacks and Palletized/Containerized Loads of Perishable and Semiperishable Subsistence

GOVERNMENT PUBLICATIONS

Federal Food, Drug, and Cosmetic Act and regulations promulgated thereunder (49 CFR Parts 171-180)

FEDERAL STANDARD

FED-STD-595 Colors Used in Government Procurement

NON-GOVERNMENTAL STANDARDS

AMERICAN SOCIETY FOR QUALITY (ASQ)

ANSI/ASQCZ1.4-1993 Sampling Procedures and Tables for Inspection by Attributes

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

- B 479 Specification for Annealed Aluminum Foil For Flexible Barrier Application
- D 1974 Standard Practice for Methods of Closing, Sealing, and Reinforcing Fiberboard Shipping Containers
- D 2103 Specification for Polyethylene Film and Sheeting
- D 5118 Standard Practice for Fabrication of Fiberboard Shipping Boxes

F 88 Seal Strength of Flexible Barrier Materials